

Chemcrete

Floor Resurfacer

GENERAL DESCRIPTION

CHEMCRETE is a specially formulated 100% solids epoxy flooring compound, used for the thick-film coating of industrial floors and secondary containment structures. Floors coated with **CHEMCRETE** are tough, abrasion and chemically resistant to a wide range of environments. **CHEMCRETE** may be overcoated with a wide range of **DUROFLOR®** products for additional chemical resistance where necessary.

FEATURES

- Good chemical resistance
- Excellent resistance to abrasion
- Easy to apply
- Self-Priming
- Economical

PACKAGING

100 ft² Kit (does not include sand)

Requires 2 x 100 lbs. bags of Wedron 480 sand

MIXING RATIO

2.7 parts base (B) to 1 part (A) hardener by weight

2 parts base (B) to 1 part (A) hardener by volume

POT LIFE

Pot life for a unit mixed with sand is about 45 minutes at 70° F. Higher temperatures or larger volumes will shorten this time. Lower temperatures or spreading out the mix will extend the pot life.

COLORS

CHEMCRETE is available in a light grey color. Other colors may be available.

TECHNICAL DATA AND INFORMATION

Basic Chemical Resistance at Room Temperature:

Inorganic Acids	Good
Organic Acids	Good
Solvents	Fair
Alkalis	Excellent
Salts	Very Good
Alcohols	Good
Hydrocarbons	Good

Typical Physical Properties of Cured System:

Density	1.25
% Solids	100
Flexural Strength @ 70°F	9,000 psi
Tensile Strength @ 70°F	7,000 psi
Tensile Adhesion @ 70°F	2,500 psi
Max. Dry Operating Temp	250°F
Compressive strength	12,000 psi
Operating pH Range	2.5-14.0

SURFACE PREPARATION

- For maximum adhesion, material should be applied to a firm, clean, dry and abraded surface.
- Clean greasy, oily or waxed surfaces with suitable solvent before applying material.
- Best results will be obtained by abrasive blasting or chemical etching the surface to remove all laitance and give a surface profile.
- Concrete may be damp but with no standing water or puddles.



QUALITY SYSTEM
REGISTERED TO
ISO 9001:2000



NSF-ISR's Registration Program
is Accredited by Member of the
IAF MLA for QMS.

MIXING & APPLICATION

Before mixing, make sure all surfaces are clean and dry. For porous, damaged, or surfaces subjected to hydrostatic pressure, it is recommended that all surfaces to be coated are first sealed with a thin film (5mils) of **DUROFLOR® SEALER**. This will prevent outgassing and provide for better adhesion.

CHEMCRETE can be applied to the **DUROFLOR SEALER** about 6-8 hours after application of the sealer, as soon as the sealer will not be disturbed by the overcoating process

Use complete units to insure correct mix ratio. Place the Base (B) portion of the Kit into a suitably sized and clean mixing container. Add the Hardener (A) to the Base (B) and mix for about 30 seconds. Once mixed, add sand to obtain the desired consistence, about ½ to ¾ to the total amount of sand recommended for the kit size. Blend until thoroughly wetted, about 1 to 2 minutes. For a dryer mix use more sand, for a more fluid mix use less sand. Material temperature should be between 70° and 95°F and surface temperature at least 40°F.

Use a trowel or screed rake to spread the mixture over the desired area. Within 5-10 minutes, broadcast the remaining sand onto the wet surface. The sand is added until rejection and no wet spots are visible. Some additional sand may be required. Clean Sandblast sand maybe used.

OVERCOATING

Vacuum, sweep, or otherwise remove all loose sand from the above surface. The resulting rough sand textured surface may be coated with a variety of topcoats, depending on the application and additional desired features.

CLEANUP

All mixing and applications tools may be cleaned with **MEK** or other suitable solvent immediately after use.

STORAGE

Store in dry area in closed containers between 50°F and 110°F. Shelf life at these conditions is greater than one year.

HEALTH AND SAFETY

READ AND UNDERSTAND ALL MATERIAL GIVEN IN THE MSDS SHEETS BEFORE USING THE PRODUCT.

CHEMCRETE DOES NOT CONTAIN ANY FLAMMABLE MATERIAL OF ANY KIND. HOWEVER, THE MATERIAL IS COMBUSTIBLE. IN THE EVENT OF A FIRE, DRY POWDER, FOAM, OR CARBON DIOXIDE FIRE EXTINGUISHERS SHOULD BE USED. FIRE FIGHTERS SHOULD WEAR RESPIRATORS.

USE PROTECTIVE GLOVES AND EYEGLASSES WHEN USING.

USE IN AREAS OF GOOD VENTILATION.

LIMITED WARRANTY

All recommendations covering the use of this product are based on past experience and laboratory findings. Methods or conditions of application and use of the product are beyond our control. We assume responsibility only for the uniformity of our product within normal manufacturing balances.

All Duromar products are formulated based on over 25 years of experience, laboratory tests, material data, field installations, and technical publications, which we believe to be, to the best of our knowledge, accurate and reliable. This information is intended to be used for guidance only. Because the only true reliable test is one that is in actual operation, Duromar will make available at no charge samples of materials for that testing purpose. Duromar, Inc. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Duromar, Inc. does, therefore, not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein is liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues, and it is, therefore, the user's responsibility to ensure that this sheet is current prior to using the product.

Rev. 11/07



QUALITY SYSTEM
REGISTERED TO
ISO 9001:2000



NSF-ISR's Registration Program
is Accredited by Member of the
IAF MLA for QMS.

706 Washington Street, Pembroke, MA 02359 USA • Tel. (781) 826-2525 • Fax (781) 826-2150

www.duromar.com