
# ASAGLEAN TECHNICAL DATA SHEET PURGING COMPOUND

# PF GRADE

Mechanical Purging Compound for Injection Molding & Extrusion

## **Packaging**



PF Grade is available in:

• 44 lb. bags (pictured above)



PICTURED: Close-up of PF Grade

# **Product Safety**

Refer to Safety Data Sheets for more information

Have a Question? Visit asaclean.com or call 800.787.4348 to speak with a purging expert.

Form #: TDS-PF Revised: 8/1/2020

## **Description & Benefits**

- High temperature purge
- Designed for super-engineering resins
- Superior cleaning power
- Suitable for hot runner cleaning
- Can be used for shutdown and sealing
- Excellent thermal stability at high processing temperatures
- No chemical reaction
- No soak time required

## **Usage Information**

Temperature Range:	280°C to 420°C (535°F to 790°F)
Minimum Clearance:	Requires 0.5 mm (0.020") clearance for hot runner gates and extrusion dies; works best if screen packs are removed, however, if not possible use the maximum 100 mesh size.
Amount of Purge:	Typically 1-2 system capacities (actual amount depends on degree of contamination)
Applications:	Injection Molding - including hot runners  Extrusion - profile, sheet, cast film & compounding
Types of Resin:	Exclusively used for purging super-engineering resins such as PPS, PEEK, ULTEM, LCP, PEI, etc.

# **Physical & Chemical Properties**

Solid
Pellets
Milky white - light yellow
Insoluble
Soluble in aromatic and ester solvents
(except for inorganic content)
Stable under normal temperatures
Non-reactive under normal handling and storage conditions
Do not exceed recommended temperature range.
Do not allow ASACLEAN PF Grade to reside in barrel for ANY
period of time at temperatures higher than 370°C (700°F).

# **Key Measurements**

Specific Gravity:	1.26 at 23°C (73°F)
Softening Point:	150°C (302°F)
Flashpoint:	460°C (860°F)
Autoignition Temp:	520°C (968°F)

Value

Please Note: The above data should be used for reference only.