
# ASAGLEAN TECHNICAL DATA SHEET

### PURGING COMPOUND

## PX2 GRADE

Mechanical Purging Compound for Injection Molding & Extrusion

#### **Packaging**



PX2 Grade is available in:

• 44 lb. bags (pictured above)



CTURED: Close-up of PX2 Grade

#### **Product Safety**

Refer to Safety Data Sheets for more information

Have a Question? Visit asaclean.com or call 800.787.4348 to speak with a purging expert.

Form #: TDS-PX2 Revised: 8/1/2020

#### **Description & Benefits**

- High temperature purge
- Designed for super-engineering resins
- Superior cleaning power
- Glass-filled
- Ideal for removing contamination
- Excellent thermal stability at high processing temperatures
- Color and material changes
- No soak time required

#### **Usage Information**

Temperature Range:	280°C to 420°C (535°F to 790°F)
Minimum Clearance:	Please speak to a Technical Sales Representative for further information on hot runner gate and extrusion die clearances.
Amount of Purge:	Typically 1-2 system capacities (actual amount depends on degree of contamination)
Applications:	Injection Molding Extrusion - profile, sheet, cast film & compounding
Types of Resin:	Exclusively used for purging super-engineering resins such as PPS, PEEK, ULTEM, LCP, PEI, etc.

### **Physical & Chemical Properties**

Physical Form:	Solid
Shape:	Pellets
Color:	Milky white - light yellow
Water Solubility:	Insoluble
Other Solvent Solubility:	Soluble in aromatic and ester solvents
	(except for inorganic content)
Stability:	Stable under normal temperatures
Reactivity:	Non-reactive under normal handling and storage conditions
Conditions to Avoid:	Do not exceed recommended temperature range.
	Do not allow ASACLEAN PX2 Grade to reside in barrel for
	ANY period of time at ANY temperature.

#### Key Measurement

Key Weasurements	Value
Specific Gravity:	1.61 at 23°C (73°F)
Softening Point:	150°C (302°F)
Flashpoint:	460°C (860°F)
Autoignition Temp:	520°C (968°F)

Please Note: The above data should be used for reference only.