

## Product Data Sheet

## BT5

**Description:** A 7 year 50 micron cast destructible vinyl film. Permanent solvent-based adhesive on a stayflat PE coated liner.

Characteristics: A 7 year cast PVC

24 hours after application vinyl label cannot be removed in

Vinyl shatters away from substrate in small pieces when removal is attempted.

**Application:** Security type labels eg: Australian Standard Approved labels, Video tape protection labels. Tamper evident applications.

**Dimensional Stability:** Excellent. No change at 48 hours at 70°C.

**Chemical Resistance:** Soaked in 5% Sulphuric Acid for 240 hours

Soaked in 5% Calcined Soda

No effect to Reference Fuel (1 hour), heptane, engine oil or

kerosene (24 hours).

**Exterior Life:** 7 years. Durability determined by substrate preparation and

maintenance of applied markings.

**Service Temperature:** -60°C to 107°C

Water Resistance: Excellent. Soaked for 240 hours in 40°C water.

Excellent. Soaked in 5% salt water for 240 hours. Salt Water Resistance:

**Heat Resistance:** No change after 240 hours at 70°C.

**Thermal Shock:** Excellent. 5 cycles of 2 hours. In 0°C to 30 minutes, in 20°C and

to 2 hours in -20°C.

**Thermal Die Cutting:** 110°C temperature. Speed 0.7

Other: No asbestos is used in the manufacture of this product.

**Humidity Resistance:** Excellent. Checked at 240 hours in 50°C at 95% RH.

## **HEAD OFFICE (SYDNEY): MELBOURNE OFFICE: BRISBANE OFFICE: AUCKLAND OFFICE:**

29 Henderson Street **TURRELLA NSW 2205** Australia

P: (02) 9556 6000 F: (02) 9556 6066 E: hvg@halifaxvogel.com.au 79-81 Wedgewood Road HALLAM VIC 3803 Australia

P: (03) 8795 0900

F: (03) 8795 0999 E: hvgmelb@halifaxvogel.com.au P: (07) 3277 6377 F: (07) 3277 6311

27 Colebard Street, West

**ACACIA RIDGE QLD 4110** 

E: hvgbris@halifaxvogel.com.au

PO Box 90721

Auckland Mail Service Centre **AUCKLAND 1030** 

New Zealand P: (09) 360 6793 F: (09) 360 2180

E: hvgnz@halifaxvogel.com.au

## www.halifaxvogel.com.au

Australia

Product Performance and Suitability: All of the descriptive information and recommendations for use of this product shall only be used as a guide. Furnishing such information in no event constitute a warranty of any kind. Buyers shall independently test and determine the suitability of the material for the purpose for which it is intended. No one is authorized to give any warranty, guarantee or make any representation in addition or contrary to the above.