

T-86 PROX-SVERS® INERT CATALYST SUPPORT BALLS

TYPICAL CHEMICAL ANALYSIS (wt. %)		T-86
Alumina, Al ₂ O ₃		18 – 28
Silica, SiO ₂		63-75
Al ₂ O ₃ + SiO ₂		≥ 91%
Calcia, CaO		< 1
Titania, TiO ₂		< 2
Alkalies, K ₂ O + Na ₂ O		1 – 4
Magnesia, MgO		< 1
Leachable Iron		< 0.001
Leachable Sulphur		None Detected
Leachable Chlorides		None Detected
TYPICAL PHYSICAL PROPERTIES		T-86
Shape		Spherical
Avg Crush Strength, lbs (kg)	1/8" (3.2 mm)	80 (36)
	1/4" (6.4 mm)	180 (82)
	3/8" (9.5 mm)	410 (186)
	1/2" (12.7 mm)	500 (227)
	5/8" (15.9 mm)	610 (277)
	3/4" (19.0 mm)	1150 (522)
	1" (25.4 mm)	2000 (907)
	1-1/4" (31.8 mm)	>2000 (907)
	1-1/2" (38.1 mm)	>2000 (907)
	2" (50.8 mm)	>2000 (907)
Loose Fill Packing Density, lbs/ft ³ (kg/m ³)		80-90 (1281 - 1442)
Apparent Particle Density, lbs/ft ³ (g/cc)		143 (2.3)
Water Absorption, wt. %		≤0.9
Hardness, Mohs'		>8
Maximum Use Temperature, ° F (° C)		1800 (982)
Mean Specific Heat, BTU/ lb-°F		0.25
UOP Pressure Shock Resistance		Passed
UOP Thermal Shock Resistance		Passed

The above data are based on controlled testing. Individual test results may vary, therefore these data may not be used for specification purposes. Average crush strength values are actual force required by a hydraulic press to break individual spheres.
NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, ARE MADE REGARDING THE DATA OR PRODUCTS SHOWN ABOVE.