

dichtol WFT Standard Spray

Product number #2087

Product description

dichtol WFT Standard Spray is a ready-to-use impregnation system based on a special polymer formulation. By applying it with the practical spray can, dichtol WFT Standard Spray enables easy and reliable impregnation of leaking components. Large pores (from 0.1 up to 0.5 mm) can be closed. This allows a high pressure tightness, even with difficult object structures. For locally known leaks, punctual impregnation ensures efficient use of material. Likewise, the direct application on site makes long waiting and delivery times unnecessary.

Characteristics

- Efficient material consumption
- Temporary corrosion protection (transport protection)
- Drinking water and food tested (hygiene institute Gelsenkirchen)

Typical applications

- capillary-active deep impregnation of micropores, hairline cracks and porosities
- Punctual serial impregnation
- Single impregnation (of large components)

Package sizes

500 ml Spray can

Storage / shelf life

Store in a cool, frost-free place (5°C up to + 20°C).
Shelf life 5 years.

Technical data

Technical data	dichtol WFT Standard Spray #2087
Application	
dip	-
brush	-
inject	-
spray	x
Surface temperature for application [max.]	40°C
Exposure time [min.]	
up to 5 mm wall thickness	4
5 - 10 mm wall thickness	8
10 - 15 mm wall thickness	13
> 15 mm wall thickness	30
Curing at + 20°C [hours]	light (full)
load-bearing capacity	
Surface drying [min.]	6
up to 5 mm wall thickness	6 (24)
5 - 10 mm wall thickness	10 (24)
10 - 15 mm wall thickness	17 (48)
> 15 mm wall thickness	24 (48)
Technical data	
Pore size [mm]	0 - 0.1
Continuous temperature resistance [°C]	-40 / +300
Short-term. Temperature resistance [°C]	-40 / +450
Viscosity DIN4 cup, + 23°C ISO 2431 (4 mm nozzle) [sec.]	13
Remaining Surface layer thickness [µm]	3

All material values are average values and vary due to the mixing ratio, the amount of material and the environmental conditions. The values stated are based on testing under normal conditions (STP) + 20°C and 1013 mbar.

Technical data sheet

Processing / Preparation

In the pores to be sealed, dirt, foreign matter, grease and other substances must be completely removed. For this we recommend the use of Diamant cleaner (# 1417).

Application

The object temperature should not exceed 40°C, otherwise the penetration of the polymer can not be guaranteed 100%.

▪ spray:

Apply dichtol in 4 steps at intervals of about 1 minute and keep moist on the surface for 5 minutes. This can penetrate dichtol pore-deep.

Curing

dichtol WFT Standard Spray physically dries out within a few hours (about 1 hour per mm wall thickness). Due to the rapid drying of dichtol, it is possible to reuse the components after a short time. See table „Technical data“.

Important note

DIAMANT guarantees the product characteristics as long as they are stored and used according to the DIAMANT instructions. DIAMANT assumes no responsibility for the processing and use of the material.

If you have further questions, our technicians are at your disposal.

Please read the safety data sheet before using the product and follow the safety instructions.

Resistance list

Chemicals	Conc. in %	WFT Standard Spray
acetate		–
acetylene		x
alkanes		x
alcohols		x
animal based oils		x
brake oil		x
citric acid		o
crude oil		x
cutting oil		x
diesel fuels		x
diethyl ether		–
engine oil		x
glycol		x
hydraulic fluid		x
hydrocarbons		x
aromatics		x
hydrochloric acid	< 20	–
hydrochloric acid	> 20	o
keton		–
kerosene		x
lubricating oil		x
machine oil		x
machinefat		x
natural gas		x
nitric acid		o
petrol		x
phthalates		o
plantbase oils		x
potassium chloride, hs		x
potassium hydroxide		x
potassium phosphate		x
salicylic acid		o
sulphuric acid	< 20	–
sulphuric acid	> 20	o

Nomenclature: hs = aqueous solution / conc. = Concentration
Symbols: x = stable / o = conditionally stable / – = unstable
The measurements were carried out at a temperature of 20°C.
Individual examinations can be carried out after consultation.

dichtol WFT Standard Spray #2087

F047/2017

Date: 29/01/2018

DIAMANT Metallplastic GmbH

Hontzlarstr. 12 – 14

41238 Mönchengladbach

GERMANY

Tel.: +49 (0)2166 – 98360

Fax: +49 (0)2166 – 83025

Mail: info@diamant-polymer.de

www.diamant-polymer.de

The listed technical data were determined under laboratory conditions and verified by quality assurance processes at the day of production. Changes are reserved and can be implemented without previous information. The customer is responsible for the verification of data topicality and should be requested before the material ordering at DIAMANT. Application, use and processing of the products happen outside of our control options and therefore lie entirely in the area of responsibility of the customer. Should nevertheless a liability come into question so is this liability limited to the value of the items delivered and used by you. We guarantee the perfect quality of our products according our general sale and delivery conditions. All technical data can differ depending on burden and operating conditions. Specific application data will be provided upon request in every individual case.